

MUJI Product Restricted Substances List (MUJI RSL)



SCOPE

- Apparel(including inner wear): Any garment worn on the body intended to protect, cover, or adorn.
- Footwear: Any durable covering for the feet intended to protect, cover, or comfort.
- Accessories(including bag): Any product intended to complement apparel, both carried and worn.
- Home Textiles: Any product intended for functional or decorative purposes in the home.
- Trim Parts: Except for the packaging materials, all the trims and accessories that sewed in the products(sewing thread, button, interlining, lining, zips, care labels, etc.)

Product Examples

The following are only examples. If you are unsure whether your product falls within the scope of this list, please contact us.

Apparel	Footwear	Accessories	Home Textiles
Shirts	Shoes	Hats	Towels
Pants/trousers	Sandals	Headbands	Bathrobes
Socks	Flip-flops	Scarves	Bedding(e.g. duvet covers, pillow covers, down duvets, mattresses, blankets, etc.)
Jackets	Boots	Bags(e.g. handbags, pouches, cases, etc)	Upholstered furniture(e.g. sofas, chairs, etc.)
Sweatshirts and hoodies	Slippers	Shoelaces	Cushions
Sweaters		Belts	Placemats
Underwear		Hair clips	Floor mops
Aprons		Gloves	Cleaning tools
		Jewelry	Felt products
		Sunglasses	Storages
		Suitcases	Laundry nets
			Pot holders/trivets

Definitions of Material Types

Natural fibers. Animal or vegetable fibers (including semi-synthetics).

Blended fibers. Woven or knitted materials created by blending two or more fiber types. For the purpose of this RSL, a blended fiber consists of a natural and a synthetic fiber.

Synthetic fibers. Human-made fibers based on synthetic chemicals (often from petroleum sources) such as polymers and extruded fibers.

Synthetic coated fabrics. Leather-like materials composed of a textile backing and, typically, a PU or PVC coating. May be referred to as artificial, imitation, vegan, or synthetic leather, or pleather.

Natural leather. Created by tanning animal rawhides.

Coating. A fluid, semi-fluid, or other material, with or without a suspension of finely divided coloring matter, which changes to a solid film when a thin layer is applied to a metal, wood, stone, paper, leather, cloth, plastic, or other surface.

Coatings do not include printing inks or those materials which actually become a part of the substrate, such as the pigment in a plastic article or those materials which are actually bonded to

the substrate, such as by electroplating or ceramic glazing. See "synthetic coated fabrics" for leather-like materials where the coating becomes part of the substrate.

Printing. The process of applying color to a fabric in definite patterns or designs.

Natural materials. Material derived from animals or plants that have undergone very little modification. Includes horn, bone, cork, wood, paper, and straw. Excludes natural fibers, natural leather, feathers, down, and metals.

Crystal. In this variety of glass, also known as lead glass, lead replaces calcium content of a typical potash glass. The addition of lead oxide gives crystal a much higher index of refraction than normal glass, and consequently much greater sparkle. Crystal typically contains at least 24% lead and is therefore exempt from many regulatory requirements for jewelry. In the European Union, labeling of crystal products is regulated by Council Directive 69/493/ EEC, which defines four categories based on the chemical composition and properties of the material.

Polymers and plastics. Plastics are composed of various polymers (typically from petroleum sources) usually mixed with additives including

colorants, plasticizers, stabilizers, and fillers. These additives affect the chemical composition, chemical properties, and mechanical properties of the plastic.

Natural rubber. Elastic material made from latex sap or trees that can be vulcanized.

Synthetic rubber. Material made from petroleum-based monomers with properties similar to natural rubber.

Foam. Spongy material made by trapping air bubbles in a solid. These can be open cell or closed cell.

Metals. Chemical elements that can be lustrous, ductile, malleable, and good conductors of heat and electricity. Includes metals deposited by physical vapor deposition (PVD), chemical vapor deposition (CVD), or electroplating.

Feathers and down. Includes the smaller down feathers as well as the larger contour and flight feathers. See the International Down and Feather Bureau for specific down and feather definitions.

Glue. A substance capable of holding materials together by surface attachment.

Examples of Materials within the Scope of the MUJI RSL

Natural Fibers Including semi synthetics	Blended Fibers	Synthetic Fibers	Synthetic Coated Fabrics	Natural Leather & Fur Skin	Coatings & Prints	Natural Materials	Other Materials	Polymers, Plastics, Foams, Natural Rubber & Synthetic Rubber	Metal	Feathers & Down	Glue
<ul style="list-style-type: none"> Cotton Wool Silk Hemp Cashmere Linen Fur hair Rayon (semi synthetic) Lyocell (semi synthetic) 	<ul style="list-style-type: none"> Cotton Polyester Wool-Nylon Ramie Polyester 	<ul style="list-style-type: none"> Polyester Acrylic Nylon Polyamide 	<ul style="list-style-type: none"> Textiles with: <ul style="list-style-type: none"> Polyurethane (PU) coating Polyvinyl Chloride (PVC) coating Other Polymeric coatings 	<ul style="list-style-type: none"> Leather Fur skin Bonded/recycled leather 	<ul style="list-style-type: none"> Printing techniques such as: <ul style="list-style-type: none"> Heat transfers Dye sublimation printing Screen printing Direct-to garment printing Discharge printing Plastisol transfers Coatings such as: <ul style="list-style-type: none"> Polyvinyl chloride (PVC) Polyurethane (PU) UV-cured 	<ul style="list-style-type: none"> Horn Bone Cork Wood Paper Straw Stone Shell (e.g. coconut or mother of pearl) Jacron (a semi-synthetic paper product) 	<ul style="list-style-type: none"> Glass Synthetic stone Porcelain Ceramic Crystal 	<ul style="list-style-type: none"> Ethylene vinyl acetate (EVA) Polystyrene (PS) Polyethylene (PE) Acrylonitrile butadiene styrene (ABS) Neoprene Polypropylene (PP) Polycarbonate (PC) Polyamide (PA) Polyurethane (PU) Polyvinyl chloride (PVC) Thermoplastic polyurethane (TPU) Thermoplastic elastomer (TPE) Styrene ethylene butylene styrene (SEBS) 	<ul style="list-style-type: none"> Stainless steel Brass Copper Gold Silver Aluminum 	<ul style="list-style-type: none"> Feathers Down 	<ul style="list-style-type: none"> Hot melt adhesive Powdered adhesive Flock adhesive Contact adhesive Latex glue Polyurethane glue Neoprene cement Epoxies Silicone adhesive UV-cured adhesive

※Includes cases where it is used as a non-woven fabric or felt.

Testing Matrix

Please refer to the AFIRM testing matrix from the link below. Please note that Per- and Polyfluoroalkyl Substances (PFAS) shall be tested for all materials except metals, ceramics, and glass.

https://afirm-group.com/wp-content/uploads/2025/11/2025_AFIRM_RSL_2025_1019.pdf

Change Log for the 2025 MUJI RSL_004

CAS No.	Substance / Material	Modification
Various	Per- and Polyfluoroalkyl Substances (PFAS)	<ul style="list-style-type: none"> Updated test method for targeted PFAS analysis in textiles and other materials to EN 17681-1:2025. The method for leather remains EN ISO 23702-1:2023. Added method for polymers: EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1) Added total fluorine method: EN 17813:2023
3147-75-9	UV Absorbers / Stabilizers	<ul style="list-style-type: none"> Added UV 329 with a 1000 ppm limit due to its inclusion on the REACH SVHC list. Dropped limit on UV 328 to 100 ppm due to new EU POP restriction.
25973-55-1		
Various	Volatile Organic Compounds (VOCs)	<ul style="list-style-type: none"> Removed 2,4-toluene diisocyanate due to boiling point and analytical issues. Included link to new AFIRM VOC Testing Guidance.

2025 MUJI RSL_004 replaces all previous versions.

Please note that changes to substances, limits and test methods compared with the previous version are highlighted in red.

SECTION 1: SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
					Limits above which test results should be reported
Acetophenone and 2-Phenyl-2-Propanol					
98-86-2	Acetophenone				
617-94-7	2-Phenyl-2-Propanol	50 ppm each	Potential breakdown products in EVA foam when using certain cross-linking agents, including Dicumyl Peroxide.	Extraction in acetone or methanol GC/MS, sonication for 30 minutes at 60° C	25 ppm each
Acidic and Alkaline Substances					
N/A	pH value	Textiles: 4.0 – 7.5 Leather: Chrome-tanned: 3.2 – 5.5 Other: 3.5 – 7.5	pH value is a characteristic number, ranging from pH 0 to pH 14, which indirectly shows the content of acidic or alkaline substances in a product. pH values less than 7 indicate sources of acidic substances, and values greater than 7 indicate sources of alkaline substances. To avoid irritation or chemical burns to the skin, the pH value of products must be in the range of human skin—approximately pH 5.5. AFIRM recommends the limits cited to comply with global regulations and to minimize the chances of Chromium VI formation during tanning and processing of leather. For chrome-tanned leather, the final fixing bath of the re-tanning process should always have a pH below 4.0 to guard against the formation of Chromium VI. Important: Egypt, Morocco, and the Gulf Cooperation Council (GCC) require pH for leather not lower than 3.5.	Textiles and synthetic coated fabrics: EN ISO 3071:2020 Leather: EN ISO 4045:2018	N/A

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Alkylphenols (APs) Alkylphenol Ethoxylates (APEOs) including all isomers					
Various	Nonylphenol (NP), mixed isomers			Textiles and Leather: EN ISO 21084:2019 Polymers and all other materials: 1 g sample/20 mL THF, sonication for 60 minutes at 70° C, analysis according to EN ISO 21084:2019 Down (China market only): GB/T 23322-2018 for compliance with GB/T 14272-2021	Total of NP + OP: 3 ppm
Various	Octylphenol (OP), mixed isomers	Total APs: 10 ppm Total APs + APEOs: 100 ppm	APEOs can be used as or found in detergents, scouring agents, spinning oils, wetting agents, softeners, emulsifying/dispersing agents for dyes and prints, impregnating agents, de-gumming for silk production, dyes and pigment preparations, polyester padding and down/feather fillings. APs are used as intermediaries in the manufacture of APEOs and antioxidants used to protect or stabilize polymers. Biodegradation of APEOs into APs is the main source of APs in the environment. APEOs and formulations containing APEOs are prohibited from use throughout supply chain and manufacturing processes. We acknowledge that residual or trace concentrations of APEOs may still be found at levels exceeding 100 ppm and that more time is necessary for the supply chain to phase them out completely. Recycled products: Contact your brand customer for information about potential exemptions from the limit on NPEOs in recycled textile products	All materials except Leather: EN ISO 18254-1:2016 with determination of APEO using LC/MS or LC/MS/MS Leather: Sample prep and analysis using EN ISO 18218-1:2023 with quantification according to EN ISO 18254-1:2016 Down (China market only): GB/T 23322-2018 for compliance with GB/T 14272-2021	Total of NPEOs + OPEOs: 20 ppm
Various	Nonylphenol ethoxylates (NPEOs)		Recycled products: Contact MUJI regarding potential exemptions from the limit on alkylphenols (APs) and alkylphenol ethoxylates (APEOs), including all isomers, in recycled textile products.		
Various	Octylphenol ethoxylates (OPEOs)				

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Azo-amines and Arylamine Salts					
92-67-1	4-Aminobiphenyl				
92-87-5	Benzidine				
95-69-2	4-Chloro-o-toluidine				
91-59-8	2-Naphthylamine				
97-56-3	o-Aminoazotoluene				
99-55-8	2-Amino-4-nitrotoluene				
106-47-8	p-Chloraniline				
615-05-4	2,4-Diaminoanisole				
101-77-9	4,4'-Diaminodiphenylmethane				
91-94-1	3,3'-Dichlorobenzidine				
119-90-4	3,3'-Dimethoxybenzidine				
119-93-7	3,3'-Dimethylbenzidine				
838-88-0	3,3'-dimethyl-4,4'-diaminodiphenylmethane		Azo dyes and pigments are colorants that incorporate one or several azo groups (-N=N-) bound with aromatic compounds.	All materials except leather: EN ISO 14362-1:2017	
120-71-8	p-Cresidine	20 ppm each	Thousands of azo dyes exist, but only those which degrade to form the listed cleaved amines are restricted.	Leather: EN ISO 17234-1:2024	5 ppm each
101-14-4	4,4'-Methylen-bis(2-chloraniline)			p-Aminoazobenzene: All materials except leather: EN ISO 14362-3:2017	
101-80-4	4,4'-Oxydianiline		Azo dyes that release these amines are regulated and should no longer be used for dyeing textiles.	Leather: EN ISO 17234-2:2011	
139-65-1	4,4'-Thiodianiline				
95-53-4	o-Toluidine				
95-80-7	2,4-Toluenediamine				
137-17-7	2,4,5-Trimethylaniline				
95-68-1	2,4 Xylidine				
87-62-7	2,6 Xylidine				
90-04-0	2-Methoxyaniline (= o-Anisidine)				
60-09-3	p-Aminoazobenzene				
3165-93-3	4-Chloro-o-toluidinium chloride				
553-00-4	2-Naphthylammoniumacetate				
39156-41-7	4-Methoxy-m-phenylene diammonium sulphate				
21436-97-5	2,4,5-Trimethylaniline hydrochloride				

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Bisphenols					
80-05-7	Bisphenol-A (BPA)	Textiles & Leather: 10 ppm Items intended to come in contact with the mouth: 1 ppm Other Materials: 1000 ppm	BPA may be used in the production of epoxy resins, polycarbonate plastics, flame retardants, and PVC. BPS may be used as a substitute for BPA and can be found along with BPF in polyamide dye-fixing agents and sulfone- and phenol- based leather tanning agents. BPA and BPS can be found in recycled polymeric and paper materials due to polycarbonate plastic and thermal receipt paper made with bisphenols entering waste streams. BPS was added to the REACH SVHC list and may need to be notified to ECHA in leather goods if found above 0.1%. Additional restrictions on the entire class of bisphenols are forthcoming with a new restriction proposal pending in the European Union. AFIRM recommends testing relevant materials for bisphenols according to the Testing Matrix and to begin working with suppliers to replace bisphenols with suitable alternatives in all products.	Leather: EN ISO 11936:2023 All other materials: Extraction: 1g sample/20 ml THF, sonication for 60 minutes at 60° C, then add methanol or acetonitrile for precipitation prior to analysis with LC/MS	
80-09-1	Bisphenol S (BPS)	Textiles: 200 ppm each Leather: 800 ppm each Limits will likely be reduced further in future revisions of the MUJI RSL based on the best available technology and feasibility within the supply chain.			Leather: 10 ppm each All other materials: 0.1 ppm for individual samples 1 ppm for composite samples
77-40-7	Bisphenol B (BPB)	Other materials: 1000 ppm each		Note for textiles: For precipitation, draw the extract to another container and add methanol or acetonitrile. Inaccurate higher results will be obtained if the textile sample contacts the precipitation solvent.	
620-92-8	Bisphenol F (BPF)	*Please submit a 'Report on the Use of Hazardous Substances' for products intentionally used, even if they fall below the specified limits.			

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Brominated & Organophosphorus Substances					
Formerly Flame Retardants					
84852-53-9	Decabromodiphenyl ethane (DBDPE)				
32534-81-9	Pentabromodiphenyl ether (PentaBDE)				
32536-52-0	Octabromodiphenyl ether (OctaBDE)				
1163-19-5	Decabromodiphenyl ether (DecaBDE)				
Various	All other Polybrominated diphenyl ethers (PBDEs)				
79-94-7	Tetrabromobisphenol A (TBBP A)				
59536-65-1	Polybromobiphenyls (PBB)				
3194-55-6	Hexabromocyclododecane (HBCDD)				
3296-90-0	2,2-bis(bromomethyl)-1,3-propanediol (BBMP)				
13674-87-8	Tris(1,3-dichloro-isopropyl) phosphate (TDCPP)				
25155-23-1	Trixylyl phosphate (TXP)				
126-72-7	Tris(2,3,-dibromopropyl) phosphate (TRIS)				
545-55-1	Tris(1-aziridinyl)phosphine oxide (TEPA)				
115-96-8	Tris(2-chloroethyl)phosphate (TCEP)				
5412-25-9	Bis(2,3-dibromopropyl) phosphate (BDBPP)				
115-86-6	Triphenyl phosphate (TPP)	500 ppm	May be used as a flame retardant, an antioxidant for PU materials, or as an alternative plasticizer to orthophthalates. Now included on the REACH SVHC list.	All materials: EN ISO 17881-2:2016	50 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Chlorinated Paraffins					
85535-84-8	Short-chain Chlorinated Paraffins (SCCPs) (C10-C13)	1000 ppm	May be used as softeners, flame retardants, or fat-liquoring agents in leather production; also as a plasticizer in polymer production.	Leather: ISO 18219-1:2021 (SCCP) ISO 18219-2:2021 (MCCP) Textiles and all other materials: ISO 22818:2021 (SCCP + MCCP)	100 ppm
85535-85-9	Medium-chain Chlorinated Paraffins (MCCPs) (C14-C17)	1000 ppm			100 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Chlorophenols					
15950-66-0	2,3,4-Trichlorophenol (TriCP)				
933-78-8	2,3,5-Trichlorophenol (TriCP)				
933-75-5	2,3,6-Trichlorophenol (TriCP)				
95-95-4	2,4,5-Trichlorophenol (TriCP)				
88-06-2	2,4,6-Trichlorophenol (TriCP)				
609-19-8	3,4,5-Trichlorophenol (TriCP)	0.5 ppm each	Chlorophenols are polychlorinated compounds used as preservatives or pesticides. Pentachlorophenol (PCP), Tetrachlorophenol (TeCP), and Trichlorophenols (TriCP) are sometimes used to prevent mold and kill insects when growing cotton and when storing/transporting fabrics. PCP, TeCP, and TriCP can also be used as in-can preservatives in print pastes and other chemical mixtures.	All materials: EN 17134-2:2023	0.5 ppm each
4901-51-3	2,3,4,5-Tetrachlorophenol (TeCP)				
58-90-2	2,3,4,6-Tetrachlorophenol (TeCP)				
935-95-5	2,3,5,6-Tetrachlorophenol (TeCP)				
87-86-5	Pentachlorophenol (PCP) and its salts and esters				

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Chlorinated Benzenes and Toluenes					
95-49-8	2-Chlorotoluene				
108-41-8	3-Chlorotoluene				
106-43-4	4-Chlorotoluene				
32768-54-0	2,3-Dichlorotoluene				
95-73-8	2,4-Dichlorotoluene				
19398-61-9	2,5-Dichlorotoluene				
118-69-4	2,6-Dichlorotoluene				
95-75-0	3,4-Dichlorotoluene				
2077-46-5	2,3,6-Trichlorotoluene				
6639-30-1	2,4,5-Trichlorotoluene				
76057-12-0	2,3,4,5-Tetrachlorotoluene				
875-40-1	2,3,4,6-Tetrachlorotoluene				
1006-31-1	2,3,5,6-Tetrachlorotoluene				
877-11-2	Pentachlorotoluene	Total: 1 ppm	<p>Chlorobenzenes and Chlorotoluenes (Chlorinated Aromatic Hydrocarbons) can be used as carriers in the dyeing process of polyester or wool/ polyester fibers. They can also be used as solvents.</p> <p>Cross-contamination from anti-moth agents and poly shipping bags may cause failures.</p> <p>Important: The Gulf Cooperation Council (GCC) maintains a limit of 1 ppm for 1,2-Dichlorobenzene in textiles.</p>	All materials: EN 17137:2024	0.2 ppm each
541-73-1	1,3-Dichlorobenzene				
106-46-7	1,4-Dichlorobenzene				
87-61-6	1,2,3-Trichlorobenzene				
120-82-1	1,2,4-Trichlorobenzene				
108-70-3	1,3,5-Trichlorobenzene				
634-66-2	1,2,3,4-Tetrachlorobenzene				
634-90-2	1,2,3,5-Tetrachlorobenzene				
95-94-3	1,2,4,5-Tetrachlorobenzene				
608-93-5	Pentachlorobenzene				
118-74-1	Hexachlorobenzene				
5216-25-1	p-Chlorobenzotrichloride				
98-07-7	Benzotrichloride				
100-44-7	Benzyl Chloride				
95-50-1	1,2-Dichlorobenzene	10 ppm			1 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Cyclosiloxanes					
556-67-2	Octamethylcyclotetrasiloxane (D4)	1000 ppm each	May be present in silicone pads and as contaminants in formulations that contain silicone, like silicone softeners and those used for prints. They are SVHCs and will be restricted from use in solvents used for dry cleaning of textiles, leather, and fur in the EU beginning 06 June 2026 with derogations.	All materials: Ultrasonic extraction with nonchlorinated organic solvent for 30 min at 40°C then GC/MS	50 ppm each
541-02-6	Decamethylcyclopentasiloxane (D5)				
540-97-6	Dodecamethylcyclohexasiloxane (D6)				
Dimethylfumarate					
624-49-7	Dimethylfumarate (DMFu)	0.1 ppm	DMFu is an anti-mold agent that may be used in sachets in packaging to prevent the buildup of mold, especially during shipping.	All materials: ISO 16186:2021	0.05 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Dyes (Forbidden and Disperse)					
2475-45-8	C.I. Disperse Blue 1				
2475-46-9	C.I. Disperse Blue 3				
3179-90-6	C.I. Disperse Blue 7				
3860-63-7	C.I. Disperse Blue 26				
56524-77-7	C.I. Disperse Blue 35A				
56524-76-6	C.I. Disperse Blue 35B				
12222-97-8	C.I. Disperse Blue 102				
12223-01-7	C.I. Disperse Blue 106				
61951-51-7	C.I. Disperse Blue 124				
23355-64-8	C.I. Disperse Brown 1	30 ppm each	Disperse dyes are a class of water-insoluble dyes that penetrate the fiber system of synthetic or manufactured fibers and are held in place by physical forces without forming chemical bonds. Disperse dyes are used in synthetic fiber (e.g., polyester, acetate, polyamide). Restricted disperse dyes are suspected of causing allergic reactions and are prohibited from use for dyeing of textiles.	All materials: DIN 54231:2022	15 ppm each
2581-69-3	C.I. Disperse Orange 1				
730-40-5	C.I. Disperse Orange 3				
82-28-0	C.I. Disperse Orange 11				
12223-33-5					
13301-61-6	C.I. Disperse Orange 37/76/59				
51811-42-8					
85136-74-9	C.I. Disperse Orange 149				
2872-52-8	C.I. Disperse Red 1				
2872-48-2	C.I. Disperse Red 11				

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Dyes, continued					
3179-89-3	C.I. Disperse Red 17				
61968-47-6	C.I. Disperse Red 151				
119-15-3	C.I. Disperse Yellow 1				
2832-40-8	C.I. Disperse Yellow 3				
6300-37-4	C.I. Disperse Yellow 7				
6373-73-5	C.I. Disperse Yellow 9				
6250-23-3	C.I. Disperse Yellow 23				
12236-29-2	C.I. Disperse Yellow 39				
54824-37-2	C.I. Disperse Yellow 49				
6858-49-7					
54077-16-6	C.I. Disperse Yellow 56				
3761-53-3	C.I. Acid Red 26				
569-61-9	C.I. Basic Red 9				
569-64-2					
2437-29-8	C.I. Basic Green 4	30 ppm each	Disperse dyes are a class of water-insoluble dyes that penetrate the fiber system of synthetic or manufactured fibers and are held in place by physical forces without forming chemical bonds. Disperse dyes are used in synthetic fiber (e.g., polyester, acetate, polyamide). Restricted disperse dyes are suspected of causing allergic reactions and are prohibited from use for dyeing of textiles.	All materials: DIN 54231:2022	15 ppm each
10309-95-2					
548-62-9	C.I. Basic Violet 3				
632-99-5	C.I. Basic Violet 14				
2580-56-5	C.I. Basic Blue 26				
1937-37-7	C.I. Direct Black 38				
2602-46-2	C.I. Direct Blue 6				
573-58-0	C.I. Direct Red 28				
16071-86-6	C.I. Direct Brown 95				
60-11-7	4-Dimethylaminoazobenzene (Solvent Yellow 2)				
6786-83-0	C.I. Solvent Blue 4				
561-41-1	4,4'-bis(dimethylamino)-4"-(methylamino)trityl alcohol				

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Dyes, Navy Blue					
118685-33-9	Component 1: C39H23ClCrN7O12S 2Na	30 ppm each	Navy blue colorants are regulated and prohibited from use for dyeing of textiles. Index 611-070-00-2	All materials: DIN 54231:2022	15 ppm each
Not allocated	Component 2: C46H30CrN10O20S2'3Na				

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Fluorinated Greenhouse Gases					
Various	See Regulation (EU) 2024/573 for a complete list.	0.1 ppm each	Prohibited from use. May be used as foam blowing agents, solvents, fire retardants, and aerosol propellants.	Sample preparation: Purge and trap — thermal desorption or SPME Measurement: GC/MS	0.1 ppm each
Formaldehyde					
50-00-0	Formaldehyde	Adults and children: 75 ppm Babies: 16 ppm	Used in textiles as an anti-creasing and anti-shrinking agent. It is also often used in polymeric resins. Important: United Arab Emirates Cabinet Resolution No. (54) restricts Formaldehyde in children's textiles to 20 ppm.	All materials except leather: JIS L 1041-2011 A (Japan Law 112) or EN ISO 14184-1:2011 Leather: EN ISO 17226-2:2019 with EN ISO 17226-1:2021 confirmation method in case of interferences. Alternatively, EN ISO 17226-1:2021 can be used on its own.	16 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Heavy Metals (Non-Jewelry) Extractable and Total Content			See Appendix A for separate South Korea KC Mark soluble Heavy Metal requirements.		
7440-36-0	Antimony (Sb)	Extractable: 30 ppm	Found in or used as a catalyst in polymerization of polyester, flame retardants, fixing agents, pigments, and alloys.	All materials except leather: DIN EN 16711-2:2016 Leather: DIN EN ISO 17072-1:2019	Extractable: 3 ppm
7440-38-2	Arsenic (As)	Extractable: 0.2 ppm Total: 100 ppm	Arsenic and its compounds can be used in preservatives, pesticides, and defoliants for cotton, synthetic fibers, paints, inks, trims, and plastics.	Extractable: All materials except leather: DIN EN 16711-2:2016 Leather: DIN EN ISO 17072-1:2019 Total: All materials except leather: DIN EN 16711-1:2016 Leather: DIN EN ISO 17072-2:2019	Extractable: 0.1 ppm Total: 10 ppm
7440-39-3	Barium (Ba)	Extractable: 1000 ppm	Barium and its compounds can be used in pigments for inks, plastics, and surface coatings, as well as in dyeing, mordants, filler in plastics, textile finishes, and leather tanning.	All materials except leather: DIN EN 16711-2:2016 Leather: DIN EN ISO 17072-1:2019	Extractable: 100 ppm
7440-43-9	Cadmium (Cd)	Extractable: 0.1 ppm Total: 40 ppm	Cadmium compounds may be used as pigments (especially in red, orange, yellow and green); as a stabilizer for PVC; and in fertilizers, biocides, and paints.	Extractable: All materials except leather: DIN EN 16711-2:2016 Leather: DIN EN ISO 17072-1:2019 Total: All materials except leather: DIN EN 16711-1:2016 Leather: DIN EN ISO 17072-2:2019	Extractable: 0.05 ppm Total: 5 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Heavy Metals (Non-Jewelry), continued			See Appendix A for separate South Korea KC Mark soluble Heavy Metal requirements.		
7440-47-3	Chromium (Cr)	Extractable: Textiles: Adults and children: 2 ppm Babies: 1 ppm	Chromium compounds can be used as dyeing additives; dye- fixing agents; colorfastness after- treatments; dyes for wool, silk, and polyamide (especially dark shades); and leather tanning. Important: Egypt restricts extractable Chromium to 2 ppm in leather products for babies and 200 ppm in leather products for other ages.	Textiles: DIN EN 16711-2:2016 Leather: EN ISO 17072-1:2019	Extractable: 0.5 ppm
18540-29-9	Chromium VI	Extractable: Leather: 3 ppm Textiles: 1 ppm	Though typically associated with leather tanning, Chromium VI also may be used in the "after-chroming" process for wool dyeing (Chrome salts applied to acid-dyed wool to improve fastness).	Textiles: DIN EN 16711-2:2016 with EN ISO 17075-1:2017 if Cr is detected Leather: EN ISO 17075-1:2017 and EN ISO 17075-2:2017 for confirmation in case the extract causes interference. Alternatively, EN ISO 17075-2:2017 may be used on its own. Ageing test: ISO 10195:2018 Method A2 is used at brand discretion.	Extractable: Leather: 3 ppm Textiles: 0.5 ppm
7440-48-4	Cobalt (Co)	Extractable: Adults: 4 ppm Children and babies: 1 ppm	Cobalt and its compounds can be used in alloys, pigments, dyestuff, and the production of plastic buttons.	All materials except leather: DIN EN 16711-2:2016 Leather: DIN EN ISO 17072-1:2019	Extractable: 0.5 ppm
7440-50-8	Copper (Cu)	Extractable: Adults: 50 ppm Children and babies: 25 ppm	Extractable: Adults: 50 ppm Children and babies: 25 ppm	All materials except leather: DIN EN 16711-2:2016 Leather: DIN EN ISO 17072-1:2019	Extractable: 5 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Heavy Metals (Non-Jewelry), continued			See Appendix A for separate South Korea KC Mark soluble Heavy Metal requirements.		
7439-92-1	Lead (Pb)	Extractable: Adults: 1 ppm Children and babies: 0.2 ppm Total: 90 ppm	May be associated with alloys, plastics, paints, inks, pigments and surface coatings. Crystal or "lead glass" is exempt from total Lead restrictions.	Extractable: All materials except leather: DIN EN 16711-2:2016 Leather: DIN EN ISO 17072-1:2019 Total: Non-metal: CPSC-CH-E1002-08.3 Metal: CPSC-CH-E1001-08.3 Lead in paint and surface coatings: CPSC-CH-E1003-09.1	Extractable: 0.2 ppm Total: 10 ppm
7439-97-6	Mercury (Hg)	Extractable: 0.02 ppm Total: 0.5 ppm	Mercury compounds can be present in pesticides and as contaminants in caustic soda (NaOH). They may also be used in paints and as catalysts in the manufacture of PU and vinyl chloride for use in PVC.	Extractable: All materials except leather: DIN EN 16711-2:2016 Leather: DIN EN ISO 17072-1:2019 Total: All materials except leather: DIN EN 16711-1:2016 Leather: DIN EN ISO 17072-2:2019	Extractable: 0.02 ppm Total: 0.1 ppm
7440-02-0	Nickel (Ni)	Extractable: 1 ppm Release (metal parts): Prolonged skin contact: 0.5 µg/cm ² /week Eyewear frames: 0.5 µg/cm ² /week	Nickel and its compounds can be used for plating alloys and improving corrosion-resistance and hardness of alloys. They can also occur as impurities in pigments and alloys.	Extractable: All materials except leather: DIN EN 16711-2:2016 Leather: DIN EN ISO 17072-1:2019 Release: EN 12472:2020 and EN 1811:2023 Release (eyewear frames): EN 16128:2015	Extractable: 0.1 ppm Release: 0.5 µg/cm ² / week
7782-49-2	Selenium (Se)	Extractable: 500 ppm	May be found in synthetic fibers, paints, inks, plastics and metal trims.	All materials except leather: DIN EN 16711-2:2016 Leather: DIN EN ISO 17072-1:2019	Extractable: 50 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Heavy Metals (Jewelry)		Sample preparation for jewelry and wearables: Wax areas not intended for skin- contact: EN 1811:2011+A1:2015			
7440-36-0	Antimony (Sb)	Paints & Coatings: Extractable: 60 ppm	Antimony and its compounds can be used as a Flame Retardant in paints, as well as a colorant in pigments.	ASTM F963-23 as referenced in ASTM F2923:2020	Extractable: 5 ppm
7440-38-2	Arsenic (As)	Paints & Coatings: Extractable: 25 ppm	Arsenic and its compounds can be used in paints and inks.	ASTM F963-23 as referenced in ASTM F2923:2020	Extractable: 5 ppm
7440-39-3	Barium (Ba)	Paints & Coatings: Extractable 1000 ppm	Barium and its compounds can be used in pigments for inks	ASTM F963-23 as referenced in ASTM F2923:2020	Extractable: 100 ppm
7440-43-9	Cadmium (Cd)	Substrates, Paints & Coatings: Total: Adults: 75 ppm Children: 40 ppm	Cadmium and its compounds are used as pigments (especially in red, orange, yellow, and green). It can also be used in alloys to improve hardness or be found as a contaminant	ASTM F963-23 as referenced in ASTM F2923:2020	Total: 5 ppm
7440-47-3	Chromium (Cr)	Paints & Coatings: Extractable: 60 ppm	Chromium and its compounds can be used as pigments in paints. It can also be used as part of alloys such as stainless steel.	ASTM F963-23 as referenced in ASTM F2923:2020	Extractable: 5 ppm
7439-92-1	Lead (Pb)	Substrates, Paints & Coatings: Total: 90 ppm	Lead and its compounds may be associated with plastics, paints, inks, pigments, and surface coatings. It can also be found in metals as a contaminant. Crystal or "lead glass" is exempt from total Lead restrictions.	ASTM F963-23 as referenced in ASTM F2923:2020	Total: 10 ppm
Heavy Metals (Jewelry), continued					
7439-97-6	Mercury (Hg)	Paints & Coatings: Extractable: 60 ppm	Mercury and its compounds may be used in paints and can be found as a contaminant in alloys and in gold due to its use during the extraction process.	ASTM F963-23 as referenced in ASTM F2923:2020	Extractable: 5 ppm
7440-02-0	Nickel (Ni)	Release (metal parts): Prolonged skin contact: 0.5 µg/cm ² /week Pierced part: 0.2 µg/cm ² /week	Nickel and its compounds can be used for plating alloys and improving the corrosion-resistance and hardness of alloys. They can also occur as impurities in pigments and alloys.	EN 12472:2020 and EN 1811:2023	Release: Prolonged skin contact: 0.5 µg/cm ² /week Pierced part: 0.2 µg/cm ² /week
7782-49-2	Selenium (Se)	Paints & Coatings: Extractable: 500 ppm	Selenium and its compounds may be found in paints and inks.	ASTM F963-23 as referenced in ASTM F2923:2020	Extractable: 50 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Monomers					
100-42-5	Styrene, Free	500 ppm	Styrene is a precursor for polymerization and may be present in various Styrene copolymers like plastic buttons. Free styrene is restricted, but total styrene is not.	Extraction in Methanol GC/MS, sonication at 60° C for 60 minutes	50 ppm
75-01-4	Vinyl Chloride	1 ppm	Vinyl Chloride is a precursor for polymerization and may be present in various PVC materials like prints, coatings, flip flops, and synthetic leather.	EN ISO 6401:2022	1 ppm
N-Nitrosamines					
62-75-9	N-nitrosodimethylamine (NDMA)	0.5 ppm each	Can be formed as by-product in the production of rubber.	EN ISO 19577:2019 with LC/MS/MS verification if positive	0.5 ppm each
55-18-5	N-nitrosodiethylamine (NDEA)				
621-64-7	N-nitrosodipropylamine (NDPA)				
924-16-3	N-nitrosodibutylamine (NDBA)				
100-75-4	N-nitrosopiperidine (NPIP)				
930-55-2	N-nitrosopyrrolidine (NPYR)				
59-89-2	N-nitrosomorpholine (NMOR)				
614-00-6	N-nitroso N-methyl N-phenylamine (NMPhA)				
612-64-6	N-nitroso N-ethyl N-phenylamine (NEPhA)				

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Organotin Compounds					
Various	Tributyltin (TBT)	0.5 ppm each			
Various	Triphenyltin (TPhT)				
Various	Dibutyltin (DBT)				
Various	Dioctyltin (DOT)				
Various	Monooctyltin (MOT)				
Various	Monobutyltin (MBT)	1 ppm each			
Various	Tricyclohexyltin (TCyHT)				
Various	Trimethyltin (TMT)				
Various	Trioctyltin (TOT)				
Various	Tripropyltin (TPT)				
Various	Dimethyltin (DMT)				
Various	Diphenyltin (DPhT)				
Various	Dipropyltin (DPT)				
Various	Monomethyltin (MMT)	Other Organotins: 1 ppm each	AFIRM recommends restricting "Other Organotins" as a matter of best practice consistent with other industry restricted substances lists.	All materials: CEN ISO/TS 16179:2012 or EN ISO 22744-1:2020	0.1 ppm each
Various	Monophenyltin (MPhT)				
1461-25-2	Tetrabutyltin (TeBT)				
597-64-8	Tetraethyltin (TeET)				
3590-84-9	Tetraoctyltin (TeOT)				
Ortho-phenylphenol					
90-43-7	Ortho-phenylphenol (OPP)	1000 ppm	OPP is used for its preservative properties in leather or as a carrier in polyester dyeing processes.	All materials : EN 17134-2:2023	100 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Ozone-depleting Substances					
Various	See Regulation (EU) 2024/590 for a complete list.	5 ppm	Prohibited from use. Ozone-depleting substances have been used as a foaming agent in PU foams as well as a dry-cleaning agent.	All materials: GC/MS headspace 120° C for 45 minutes	5 ppm
Per- and Polyfluoroalkyl Substances (PFAS)					
Various	All PFAS as measured by total organic fluorine	50 ppm	PFAS may be used in commercial water-, oil-, and stain-repellent agents as well as in breathable membranes that remove moisture, e.g., PTFE. Refer to Appendix B for a list of PFAS substances and CAS Numbers for which testing can be conducted to indicate whether PFAS chemistry is present above restricted levels due to intended use or unintended contamination. See AFIRM PFAS Phaseout Guidance for a recommended testing approach to ensure compliance with all global regulations using the methods included in this section. Recycled products: Contact MUJI about potential exemptions from the limit on total organic fluorine in recycled textile products.	EN 14582:2016 or ASTM D7359:2023 Methods quantify total fluorine (inorganic + organic). See AFIRM PFAS Phaseout Guidance for additional information about total versus total organic fluorine.	20 ppm for individual sample 50 ppm for max. composite of two samples
Various	Perfluorooctane Sulfonate (PFOS) and its salts	25 ppb total		Textiles and other materials (excluding polymers): EN 17681-1:2025 Leather: EN ISO 23702-1:2023 Polymers (synthetic coated fabrics & polymers, plastics, foams, natural & synthetic rubber): EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1). Significantly higher findings of PFAS analytes are possible with EN 17681-1:2025, especially FTOHs, which does not necessarily mean PFAS were intentionally used. Check with MUJI to understand whether re-tests of previously tested materials are necessary.	25 ppb total
Various	PFOS-related substances	1000 ppb total			1000 ppb total
Various	Perfluorooctanoic Acid (PFOA) and its salts	25 ppb total			25 ppb total
Various	PFOA-related substances	1000 ppb total			1000 ppb total
Various	Perfluorohexane-1-sulphonic acid (PFHxS) and its salts	25 ppb total			25 ppb total
Various	PFHxS-related substances	1000 ppb total			1000 ppb total
Various	C9-C14 Perfluorocarboxylic acids (PFCAs) and their salts	25 ppb total			25 ppb total
Various	C9-C14 PFCA-related substances	260 ppb total			260 ppb
Various	PFHxA and its salts	25 ppb total			25 ppb total
Various	PFHxA-related substances	1000 ppb total			1000 ppb total

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Pesticides and Herbicides, Agricultural					
Various	See Appendix C for a complete list.	0.5 ppm each	May be found in natural fibers, primarily cotton.	All materials: EN ISO 15913:2003 or EPA 8081/EPA 8151A or BVL L 00.00- 34:2010-09	0.5 ppm each

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Phthalates					
28553-12-0	Di-Iso-nonylphthalate (DINP)				
117-84-0	Di-n-octylphthalate (DNOP)				
117-81-7	Di(2-ethylhexyl)-phthalate (DEHP)				
26761-40-0	Diisodecylphthalate (DIDP)				
85-68-7	Butylbenzylphthalate (BBP)				
84-74-2	Dibutylphthalate (DBP)				
84-69-5	Diisobutylphthalate (DIBP)				
84-75-3	Di-n-hexylphthalate (DnHP)				
84-66-2	Diethylphthalate (DEP)				
131-11-3	Dimethylphthalate (DMP)				
131-18-0	Di-n-pentyl phthalate (DPENP)				
84-61-7	Dicyclohexyl phthalate (DCHP)				
71888-89-6	1,2-Benzenedicarboxylic acid, di-C6-8-branched alkyl esters, C7-rich	500 ppm each Total: 1000 ppm	<p>Esters of ortho-phthalic acid (Phthalates) are a class of organic compound commonly added to plastics to increase flexibility. They are sometimes used to facilitate the molding of plastic by decreasing its melting temperature.</p> <p>Phthalates can be found in:</p> <ul style="list-style-type: none"> Flexible plastic components (e.g., PVC) Print pastesxx Adhesives Plastic buttons Plastic sleeveings Polymeric coatings 	<p>Sample preparation for all materials: CPSC-CH-C1001-09.4</p> <p>Measurement:</p> <p>Textiles: GC/MS, EN ISO 14389:2014 (7.1 Calculation based on weight of print only; 7.2 Calculation based on weight of print and textile if print cannot be removed).</p> <p>All materials except textiles: GC/MS</p>	50 ppm each
117-82-8	Bis(2-methoxyethyl) phthalate				
605-50-5	Diisopentyl phthalate (DIPP)				
131-16-8	Dipropyl phthalate (DPRP)				
27554-26-3	Diisoctyl phthalate (DIOP)				
68515-50-4	1,2-Benzenedicarboxylic acid, dihexyl ester, branched and linear				
71850-09-4	Diisohexyl phthalate (DIHxP)				
68515-42-4	1,2-Benzenedicarboxylic acid, di-C7-11-branched and linear alkyl esters (DHNUP)				
84777-06-0	1,2-Benzenedicarboxylic acid Dipentyl ester, branched and linear				
68648-93-1	1,2-Benzenedicarboxylic acid, di-C6-10-alkyl esters or mixed decyl and hexyl and octyl diesters with ³ 0.3% of dihexyl phthalate; 1,2-Benzenedicarboxylic acid, mixed decyl and hexyl and octyl diesters;				
68515-51-5	1,2-Benzenedicarboxylic acid, di-C6-10-alkyl esters				
776297-69-9	n-Pentyl-isopentylphthalate (nPIPP)				
26040-51-7	Bis(2-ethylhexyl) tetrabromophthalate				

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Polycyclic Aromatic Hydrocarbons (PAHs)					
83-32-9	Acenaphthene				
208-96-8	Acenaphthylene				
120-12-7	Anthracene				
191-24-2	Benzo(g,h,i)perylene				
86-73-7	Fluorene	①No individual restriction ① + ② = Total: 10 ppm	PAHs are natural components of crude oil and are common residues from oil refining. PAHs have a characteristic smell similar to that of car tires or asphalt. Oil residues containing PAHs are added to rubber and plastics as a softener or extender and may be found in rubber, plastics, lacquers and coatings. PAHs are often found in the outsoles of footwear and in printing pastes for screen prints. PAHs can be present as impurities in Carbon Black. They also may be formed from thermal decomposition of recycled materials during reprocessing	All materials: AFPS GS 2019 or EN 17132:2019 or ISO 16190:2021	0.2 ppm each
206-44-0	Fluoranthene				
193-39-5	Indeno(1,2,3-cd)pyrene				
91-20-3	Naphthalene**				
85-01-8	Phenanthrene				
129-00-0	Pyrene				
56-55-3	Benzo(a)anthracene				
50-32-8	Benzo(a)pyrene				
205-99-2	Benzo(b)fluoranthene				
192-97-2	Benzo[e]pyrene	②1 ppm each Child care articles: 0.5 ppm each ① + ② = Total: 10 ppm	Naphthalene: Dispersing agents for textile dyes may contain high residual Naphthalene concentrations due to the use of low-quality Naphthalene derivatives (e.g., poor-quality Naphthalene Sulphonate Formaldehyde condensation products).		
205-82-3	Benzo[j]fluoranthene				
207-08-9	Benzo(k)fluoranthene				
218-01-9	Chrysene				
53-70-3	Dibenzo(a,h)anthracene				
Quinoline					
91-22-5	Quinoline	50 ppm	Found as an impurity in polyester and some dyestuffs. Quinoline can be included with disperse dye testing, as the same method is used for both. It is not expected in non-dyed materials.	All materials: DIN 54231:2022 with methanol extraction at 70° C	10 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Solvents and Residuals					
68-12-2	Dimethylformamide (DMFa)	500 ppm	Solvent used in plastics, rubber, and polyurethane (PU) coating. Water-based PU does not contain DMFa and is therefore preferable.	Textiles: EN 17131:2019 All other materials: ISO 16189:2021	50 ppm each
75-12-7	Formamide	1000 ppm each	Byproduct in the production of EVA foams. Taiwan CNS 15493: BSMI may enforce a limit of 200 ppm in yoga mats under authority of the Consumer Protection Act.		
127-19-5	Dimethylacetamide (DMAc)		Solvent used in the production of elastane fibers and sometimes as substitute for DMFa.		
872-50-4	N-Methyl-2-pyrrolidone (NMP)		Industrial solvent used in production of water-based polyurethanes and other polymeric materials. May also be used as a surface treatment for textiles, resins, and metal-coated plastics, or as a paint stripper.		
UV Absorbers / Stabilizers					
3846-71-7	UV 320	1000 ppm each	PU foam materials such as open cell foams for padding. Used as UV Absorbers for plastics (PVC, PET, PC, PA, ABS, and other polymers), rubber, polyurethane.	ISO 24040:2022 with extraction in THF, analysis by GC/MS	100 ppm each
3864-99-1	UV 327				50 ppm
3896-11-5	UV 326				100 ppm
3147-75-9	UV 329				
36437-37-3	UV 350				
25973-55-1	UV 328	100 ppm	Used as UV Absorbers for plastics (PVC, PET, PC, PA, ABS, and other polymers), rubber, and polyurethane.		
2440-22-4	Drometrizole	For informational purposes only. AFIRM recommends testing to assess content levels.			

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Volatile Organic Compounds (VOCs)					
71-43-2	Benzene	5 ppm			Benzene: 5 ppm
Various	Other: See Appendix D for a complete list.	Total: 500 ppm	<p>The VOCs in Appendix D represent a broad range of potentially harmful substances that can be semiquantified using the prescribed headspace method. Upon conducting this test, substances that also appear in other sections of the RSL with specific test methods and limit values may be detected, and further testing may be appropriate to assess product conformance. The substances in Appendix D should not be used in textile auxiliary chemical preparations. They are associated with solvent-based processes such as solvent- based polyurethane coatings, glues/ adhesives, and polymer manufacturing. They should not be used for any kind of facility or spot cleaning. Individual VOCs should be reported if found > 100 ppm and confirmation testing may be required, especially for substances also included in other sections of the RSL with dedicated limits.</p> <p>See AFIRM VOC Testing Guidance for additional information.</p>	<p>For general VOC screening: GC/MS headspace 45 minutes at 120° C</p>	<p>Other: 100 ppm each</p>

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Appendix A. South Korea KC Mark Soluble Heavy Metal Requirements					
NOTE: South Korea KC Mark requirements apply to the migration of Heavy Metals from surface coatings/paints, synthetic resins, and paper materials in products intended to be placed in the mouth of children and products intended for infants.					
7440-36-0	Antimony (Sb)	60 ppm	Found in or used as a catalyst in polymerization of polyester, flame retardants, fixing agents, pigments, and alloys.	ISO 8124-3:2020 with Amendment 1 of 202	-
7440-38-2	Arsenic (As)	25 ppm	Arsenic and its compounds can be used in preservatives, pesticides, and defoliants for cotton, synthetic fibers, paints, inks, trims, and plastics.		
7440-39-3	Barium (Ba)	1000 ppm	Barium and its compounds can be used in pigments for inks, plastics, and surface coatings, as well as in dyeing, mordants, filler in plastics, textile finishes, and leather tanning.		
7440-43-9	Cadmium (Cd)	75 ppm	Cadmium compounds may be used as pigments (especially in red, orange, yellow and green); as a stabilizer for PVC; and in fertilizers, biocides, and paints.		
7440-47-3	Chromium (Cr)	60 ppm	Chromium compounds can be used as dyeing additives; dye- fixing agents; colorfastness after- treatments; dyes for wool, silk, and polyamide (especially dark shades); and leather tanning.		
7439-92-1	Lead (Pb)	90 ppm	May be associated with alloys, plastics, paints, inks, pigments and surface coatings.		
7439-97-6	Mercury (Hg)	60 ppm	Mercury compounds can be present in pesticides and as contaminants in caustic soda (NaOH). They may also be used in paints and as catalysts in the manufacture of PU and vinyl chloride for use in PVC.		
7782-49-2	Selenium (Se)	500 ppm	May be found in synthetic fibers, paints, inks, plastics and metal trims.		

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Appendix B. Per- and Polyfluoroalkyl Substances (PFAS)					
NOTE: This list is a subset of PFAS and is not exhaustive. Findings would indicate intentional use or significant contamination.					
PFOS and Its Salts					
1763-23-1	Perfluorooctanesulfonic acid (PFOS)	Total:25 ppb	-	Textiles and other materials (excluding polymers): EN 17681-1:2025 Leather: EN ISO 23702-1:2023 Polymers (synthetic coated fabrics & polymers, plastics, foams, natural & synthetic rubber): EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1).	Total:25 ppb
PFOS-related Substances					
4151-50-2	N-Ethylperfluoro-1-octanesulfonamide (N-Et-FOSA)	Total: 1000 ppb	-	Textiles and other materials (excluding polymers): EN 17681-1:2025 Leather: EN ISO 23702-1:2023 Polymers (synthetic coated fabrics & polymers, plastics, foams, natural & synthetic rubber): EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1).	Total: 1000 ppb
31506-32-8	N-Methylperfluoro-1-octanesulfonamide (N-Me-FOSA)	Total: 1000 ppb	-		Total: 1000 ppb
1691-99-2	2-(N-Ethylperfluoro-1-octanesulfonamido)-ethanol (N-Et-FOSE)	Total: 1000 ppb	-		Total: 1000 ppb
24448-09-7	2-(N-Methylperfluoro-1-octanesulfonamido)-ethanol (N-Me-FOSE)	Total: 1000 ppb	-		Total: 1000 ppb
307-35-7	Perfluoro-1-octanesulfonyl fluoride (POSF)	Total: 1000 ppb	-		Total: 1000 ppb
754-91-6	Perfluorooctane sulfonamide (PFOSA)	Total: 1000 ppb	-		Total: 1000 ppb

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
PFOA and Its Salts					
335-67-1	Perfluorooctanoic acid (PFOA)	Total:25 ppb	-	Textiles and other materials (excluding polymers): EN 17681-1:2025 Leather: EN ISO 23702-1:2023 Polymers (synthetic coated fabrics & polymers, plastics, foams, natural & synthetic rubber): EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1).	Total:25 ppb
PFOA-related Substances					
39108-34-4	1H,1H,2H,2H-Perfluorodecanesulfonic acid (8:2 FTS)	Total: 1000 ppb	-	Textiles and other materials (excluding polymers): EN 17681-1:2025 Leather: EN ISO 23702-1:2023 Polymers (synthetic coated fabrics & polymers, plastics, foams, natural & synthetic rubber): EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1).	Total: 1000 ppb
376-27-2	Methyl perfluorooctanoate (Me-PFOA)*1	Total: 1000 ppb	-		Total: 1000 ppb
3108-24-5	Ethyl perfluorooctanoate (Et-PFOA)*1	Total: 1000 ppb	-		Total: 1000 ppb
678-39-7	2-Perfluorooctylethanol (8:2 FTOH)	Total: 1000 ppb	-		Total: 1000 ppb
27905-45-9	1H,1H,2H,2H-Perfluorodecyl acrylate (8:2 FTA)*2	Total: 1000 ppb	-		Total: 1000 ppb
1996-88-9	1H,1H,2H,2H-Perfluorodecyl methacrylate (8:2 FTMA)*2	Total: 1000 ppb	-		Total: 1000 ppb

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
PFHxS and Its Salts					
355-46-4	Perfluorohexane Sulfonic acid (PFHxS)	Total: 25 ppb	-	Textiles and other materials (excluding polymers): EN 17681-1:2025 Leather: EN ISO 23702-1:2023 Polymers (synthetic coated fabrics & polymers, plastics, foams, natural & synthetic rubber): EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1).	Total: 25 ppb
PFHxS-related Substances					
68259-15-4	N-Methylperfluoro-1-hexanesulfonamide (N-Me-FHxSA)	Total: 1000 ppb	-	Textiles and other materials (excluding polymers): EN 17681-1:2025 Leather: EN ISO 23702-1:2023 Polymers (synthetic coated fabrics & polymers, plastics, foams, natural & synthetic rubber): EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1).	Total: 1000 ppb
41997-13-1	Perfluorohexane sulfonamide (PFHxSA)	Total: 1000 ppb	-	Textiles and other materials (excluding polymers): EN 17681-1:2025 Leather: EN ISO 23702-1:2023 Polymers (synthetic coated fabrics & polymers, plastics, foams, natural & synthetic rubber): EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1).	Total: 1000 ppb

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
C9 – C14 PFCAs and Their Salts					
375-95-1	Perfluorononanoic Acid (PFNA, C9-PFCA)	Total:25 ppb	-	Textiles and other materials (excluding polymers): EN 17681-1:2025 Leather: EN ISO 23702-1:2023 Polymers (synthetic coated fabrics & polymers, plastics, foams, natural & synthetic rubber): EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1).	Total:25 ppb
335-76-2	Perfluorodecanoic Acid (PFDA, C10-PFCA)	Total:25 ppb	-		Total:25 ppb
2058-94-8	Perfluoroundecanoic Acid (PFUnA, C11-PFCA)	Total:25 ppb	-		Total:25 ppb
307-55-1	Perfluorododecanoic Acid (PFDoA, C12-PFCA)	Total:25 ppb	-		Total:25 ppb
72629-94-8	Perfluorotridecanoic Acid (PFTrDA, C13-PFCA)	Total:25 ppb	-		Total:25 ppb
376-06-7	Perfluorotetradecanoic Acid (PFTeDA, C14-PFCA)	Total:25 ppb	-		Total:25 ppb
172155-07-6	Perfluoro-3-7-dimethyloctanecarboxylate (PF-3,7-DMOA)	Total:25 ppb	-		Total:25 ppb
C9 – C14 PFCA-related Substances					
17741-60-5	1H,1H,2H,2H-Perfluorododecyl acrylate (10:2 FTA)*2	Total:260 ppb	-	Textiles and other materials (excluding polymers): EN 17681-1:2025 Leather: EN ISO 23702-1:2023 Polymers (synthetic coated fabrics & polymers, plastics, foams, natural & synthetic rubber): EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1).	Total:260 ppb
2144-54-9	1H,1H,2H,2H-Perfluorododecyl methacrylate (10:2 FTMA)*2	Total:260 ppb	-		Total:260 ppb
865-86-1	1H,1H,2H,2H-Perfluorododecanol (10:2 FTOH)	Total:260 ppb	-		Total:260 ppb
34598-33-9	2H,2H,3H,3H-Perufluoroundecanoic acid (H4PFUnA)	Total:260 ppb	-		Total:260 ppb
678-39-7	Perfluorocylethanol 8:2 (8:2 FTOH)	Total:260 ppb	-		Total:260 ppb
39239-77-5	1H,1H,2H,2H-perfluorotetradecan-1-ol (12:2 FTOH)	Total:260 ppb	-		Total:260 ppb
120226-60-0	1H,1H,2H,2H-Perfluorododecanesulphonic acid (10:2 FTS)	Total:260 ppb	-		Total:260 ppb

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
PFHxA, its salts					
307-24-4	Perfluorohexanoic Acid (PFHxA, C6-PFCA)	Total:25 ppb	-	Textiles and other materials (excluding polymers): EN 17681-1:2025 Leather: EN ISO 23702-1:2023 Polymers (synthetic coated fabrics & polymers, plastics, foams, natural & synthetic rubber): EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1).	Total:25 ppb
PFHxA-related substances					
17527-29-6	1H,1H,2H,2H-Perfluorooctyl acrylate (6:2 FTA)*2	Total: 1000 ppb	-	Textiles and other materials (excluding polymers): EN 17681-1:2025	Total: 1000 ppb
2144-53-8	1H,1H,2H,2H-Perfluorooctyl methacrylate (6:2 FTMA)*2	Total: 1000 ppb	-	Leather: EN ISO 23702-1:2023 Polymers (synthetic coated fabrics & polymers, plastics, foams, natural & synthetic rubber): EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1).	Total: 1000 ppb
27619-97-2	1H,1H,2H,2H-Perfluorooctanesulfonic acid (6:2 FTS)	Total: 1000 ppb	-		Total: 1000 ppb
647-42-7	1H,1H,2H,2H-Perfluorooctanol (6:2 FTOH)	Total: 1000 ppb			Total: 1000 ppb
<p>NOTE: The substances in red are included as they appear in the regulation. However, as they are hydrolysed during the testing, they will never be detected or reported. Instead, they will be reported as the related substances as shown, each of which is also included in the regulation.</p> <p>*1:Hydrolyzed to PFOA. *2:Hydrolyzed to x:2 FTOH under hydrolysis conditions.</p>					

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Appendix C. Pesticides and Herbicides, Agricultural					
93-72-1	2-(2,4,5-trichlorophenoxy) propionic acid, its salts and compounds; 2,4,5-TP	0.5 ppm	May be found in natural fibers, primarily cotton.	All material: EN ISO 15913:2003 or EPA 8081/EPA 8151A or BVL L 00.00-34:2010-09	0.5 ppm
93-76-5	2,4,5-T	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
94-75-7	2,4-D	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
309-00-2	Aldrine	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
86-50-0	Azinophosmethyl	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
2642-71-9	Azinophosethyl	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
4824-78-6	Bromophos-ethyl	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
2425-06-1	Captafol	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
63-25-2	Carbaryl	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
510-15-6	Chlorbenzilat	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
57-74-9	Chlordane	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
6164-98-3	Chlordimeform	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
470-90-6	Chlorfenvinphos	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
1897-45-6	Chlorthalonil	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
56-72-4	Coumaphos	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
68359-37-5	Cyfluthrin	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
91465-08-6	Cyhalothrin	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
52315-07-8	Cypermethrin	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Appendix C. Pesticides and Herbicides, Agricultural , continued					
78-48-8	S,S,S-Tributyl phosphorothioate (Tribufos)	0.5 ppm	May be found in natural fibers, primarily cotton.	All material: EN ISO 15913:2003 or EPA 8081/EPA 8151A or BVL L 00.00-34:2010-09	0.5 ppm
52918-63-5	Deltamethrin	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
53-19-0	DDD	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
72-54-8	DDE	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
3424-82-6	DDT	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
72-55-9	Diazinone	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
50-29-3	Dichlofluanide	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
789-02-6	Dichloroprop	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
115-32-2	Dicofol	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
141-66-2	Dicrotophos	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
60-57-1	Dieldrine	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
60-51-5	Dimethoate	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
88-85-7	Dinoseb, its salts and acetate	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
63405-99-2	DTTB (4, 6-Dichloro-7 (2,4,5-trichlorophenoxy)-2-Trifluoro methyl benz imidazole)	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
115-29-7	Endosulfan	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
959-98-8	Endosulfan I (alpha)	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
33213-65-9	Endosulfan II (beta)	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
72-20-8	Endrine	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Appendix C. Pesticides and Herbicides, Agricultural , continued					
66230-04-4	Esfenvalerate	0.5 ppm	May be found in natural fibers, primarily cotton.	All material: EN ISO 15913:2003 or EPA 8081/EPA 8151A or BVL L 00.00-34:2010-09	0.5 ppm
106-93-4	Ethylen dibromid	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
56-38-2	Ethylparathione; Parathion	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
51630-58-1	Fenvalerate	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
Various	Halogenated naphthalenes, including polychlorinated naphthalenes (PCNs)	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
76-44-8	Heptachlor	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
1024-57-3	Heptachloroepoxide	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
36355-01-8	Hexabromobiphenyl	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
319-84-6	<i>a</i> -Hexachlorocyclohexane with & without Lindane	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
319-85-7	<i>b</i> -Hexachlorocyclohexane with & without Lindane	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
319-86-8	<i>g</i> -Hexachlorocyclohexane with & without Lindane	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
118-74-1	Hexachlorobenzene	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
465-73-6	Isodrine	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
4234-79-1	Kelevane	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
143-50-0	Kepone	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
58-89-9	Lindane	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
121-75-5	Malathione	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
94-74-6	MCPA	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
94-81-5	MCPB	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Appendix C. Pesticides and Herbicides, Agricultural , continued					
93-65-2	Mecoprop	0.5 ppm	May be found in natural fibers, primarily cotton.	All material: EN ISO 15913:2003 or EPA 8081/EPA 8151A or BVL L 00.00-34:2010-09	0.5 ppm
10265-92-6	Metamidophos	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
72-43-5	Methoxychlor	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
2385-85-5	Mirex	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
6923-22-4	Monocrotophos	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
298-00-0	Parathion-methyl	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
1825-21-4	Pentachloroanisole	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
7786-34-7	Phosdrin/Mevinphos	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
72-56-0	Perthane	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
31218-83-4	Propethamphos	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
41198-08-7	Profenophos	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
13593-03-8	Quinalphos	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
82-68-8	Quintozene	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
8001-50-1	Strobane	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
297-78-9	Telodrine	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
8001-35-2	Toxaphene	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
731-27-1	Tolylfluanide	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm
1582-09-8	Trifluraline	0.5 ppm	May be found in natural fibers, primarily cotton.		0.5 ppm

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Appendix D. Volatile Organic Compounds (VOCs)					
75-15-0	Carbon Disulfide	Total: 500 ppm			100 ppm each
56-23-5	Carbon Tetrachloride	Total: 500 ppm			100 ppm each
67-66-3	Chloroform	Total: 500 ppm			100 ppm each
108-94-1	Cyclohexanone	Total: 500 ppm			100 ppm each
107-06-2	1,2-Dichloroethane	Total: 500 ppm			100 ppm each
75-35-4	1,1-Dichloroethylene	Total: 500 ppm			100 ppm each
100-41-4	Ethylbenzene	Total: 500 ppm			100 ppm each
76-01-7	Pentachloroethane	Total: 500 ppm			100 ppm each
630-20-6	1,1,1,2- Tetrachloroethane	Total: 500 ppm			100 ppm each
79-34-5	1,1,2,2- Tetrachloroethane	Total: 500 ppm			100 ppm each
127-18-4	Tetrachloroethylene (PERC)	Total: 500 ppm			100 ppm each
108-88-3	Toluene	Total: 500 ppm			100 ppm each
71-55-6	1,1,1- Trichloroethane	Total: 500 ppm			100 ppm each
79-00-5	1,1,2- Trichloroethane	Total: 500 ppm			100 ppm each
79-01-6	Trichloroethylene	Total: 500 ppm			100 ppm each
1330-20-7	Xylenes (meta-, ortho-, para-)	Total: 500 ppm			100 ppm each
108-38-3		Total: 500 ppm			100 ppm each
95-47-6		Total: 500 ppm			100 ppm each
106-42-3		Total: 500 ppm			100 ppm each
95-50-1	1,2-Dichlorobenzene	Total: 500 ppm			100 ppm each
106-46-7	1,4-Dichlorobenzene	Total: 500 ppm			100 ppm each
872-50-4	1-Methyl-2-pyrrolidione	Total: 500 ppm			100 ppm each
617-94-7	2-phenyl-2-propanol	Total: 500 ppm			100 ppm each
The VOCs in Appendix D represent a broad range of potentially harmful substances that can be semiquantified using the prescribed headspace method. Upon conducting this test, substances that also appear in other sections of the RSL with specific test methods and limit values may be detected, and further testing may be appropriate to assess product conformance. The substances in Appendix D should not be used in textile auxiliary chemical preparations. They are associated with solvent-based processes such as solvent- based polyurethane coatings, glues/ adhesives, and polymer manufacturing. They should not be used for any kind of facility or spot cleaning. Individual VOCs should be reported if found > 100 ppm and confirmation testing may be required, especially for substances also included in other sections of the RSL with dedicated limits. See AFIRM VOC Testing Guidance for additional information.					
For general VOC screening: GC/MS headspace 45 minutes at 120° C					

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Appendix D. Volatile Organic Compounds (VOCs) , continued					
98-86-2	Acetophenone	Total: 500 ppm	The VOCs in Appendix D represent a broad range of potentially harmful substances that can be semiquantified using the prescribed headspace method. Upon conducting this test, substances that also appear in other sections of the RSL with specific test methods and limit values may be detected, and further testing may be appropriate to assess product conformance. The substances in Appendix D should not be used in textile auxiliary chemical preparations. They are associated with solvent-based processes such as solvent- based polyurethane coatings, glues/ adhesives, and polymer manufacturing. They should not be used for any kind of facility or spot cleaning. Individual VOCs should be reported if found > 100 ppm and confirmation testing may be required, especially for substances also included in other sections of the RSL with dedicated limits. <i>See AFIRM VOC Testing Guidance for additional information.</i>	For general VOC screening: GC/MS headspace 45 minutes at 120° C	100 ppm each
75-12-7	Formamide	Total: 500 ppm			100 ppm each
127-19-5	N,N-Dimethylacetamide (DMAC)	Total: 500 ppm			100 ppm each
91-20-3	Naphthalene	Total: 500 ppm			100 ppm each
68-12-2	N-N-Dimethylformamide (DMFa)	Total: 500 ppm			100 ppm each
100-42-5	Styrene	Total: 500 ppm			100 ppm each
96-18-4	1,2,3-trichloropropane	Total: 500 ppm			100 ppm each
78-87-5	1,2-Dichloropropane	Total: 500 ppm			100 ppm each
111-15-9	2-Ethoxyethyl acetate	Total: 500 ppm			100 ppm each
149-57-5	2-Ethylhexane acid	Total: 500 ppm			100 ppm each
62-53-3	Aniline	Total: 500 ppm			100 ppm each
111-96-6	Bis(2-methoxyethyl)ether	Total: 500 ppm			100 ppm each
78-59-1	Isophorone	Total: 500 ppm			100 ppm each
108-95-2	Phenol	Total: 500 ppm			100 ppm each
109-99-9	THF	Total: 500 ppm			100 ppm each
106-94-5	1-bromopropane	Total: 500 ppm			100 ppm each
70657-70-4	1-PG2MEA 1-Propanol,2-methoxy-, acetate)	Total: 500 ppm			100 ppm each

SECTION 1 : SUBSTANCES PROHIBITED OR REGULATED BY LAW

CAS No.	Substance	MUJI Limits	Potential Uses & Additional Information	Suitable Test Method	Reporting Limit
Appendix D. Volatile Organic Compounds (VOCs) , continued					
111-77-3	2-(2-Methoxyethoxy)ethanol	Total: 500 ppm			100 ppm each
110-80-5	2-ethoxyethanol	Total: 500 ppm			100 ppm each
109-86-4	2-Methoxyethanol EGME (ethylene glycol monomethyl ether)	Total: 500 ppm			100 ppm each
1589-47-5	2-Methoxypropan-1-ol	Total: 500 ppm			100 ppm each
110-71-4	EGDME (Ethylene glycol dimethyl ether)	Total: 500 ppm			100 ppm each
110-49-6	EGMEA (Ethylene glycol monomethyl ether acetate)	Total: 500 ppm			100 ppm each
67-72-1	Hexachloroethane	Total: 500 ppm			100 ppm each
75-09-2	Merhylene chloride (dichloromethane)	Total: 500 ppm			100 ppm each
110-54-3	n-hexane	Total: 500 ppm			100 ppm each
112-49-2	TEGDME(Triethylene glycol dimethyl ether)	Total: 500 ppm	See AFIRM VOC Testing Guidance for additional information.	For general VOC screening: GC/MS headspace 45 minutes at 120° C	100 ppm each

SECTION 2 : OTHER LIMITS & RESTRICTIONS

CAS No.	Restricted Substances List	Requirement
Various	California Proposition 65 https://oehha.ca.gov/proposition-65/proposition-65-list/	Please submit the 'Report on the Use of Hazardous Substances' to Ryohin Keikaku if substances found on the the list are identified in materials or products.
Various	(SVHCs)/EU–REACH Substance of Very High Concern List https://www.echa.europa.eu/candidate-list-table	Ryohin Keikaku requests its suppliers to comply with the Substances of Very High Concern (SVHC) list based on REACH, the EU chemical substances regulation. Please submit the 'Report on the Use of Hazardous Substances' to Ryohin Keikaku if any substance(s) in materials or products contain more than 0.1% (w/w).
53306-54-0	Suitable Test Method Sample preparation for all materials: CPSC-CH-C1001-09.4 Measurement: Textiles: GC/MS, EN ISO 14389:2022 (8.1 Calculation based on weight of print only; 8.2 Calculation based on weight of print and textile if print cannot be removed). All materials except textiles: GC/MS Reporting Limit: 50 ppm	For informational purposes only. Ryohin Keikaku recommends testing to assess content levels. Please submit the 'Report on the Use of Hazardous Substances' to Ryohin Keikaku for intentional use of this substance regardless of concentration.